



### Product Description

Colour Index Name	Pigment Yellow 34
Colour Index No.	77600
CAS number	1344-37-2
Chemical name	Lead Chromate / Middle Chrome

### Structural Formula



### Physical Properties

Parameter	Values	Method
Specific gravity	5.4 gm/cm <sup>3</sup>	IS 33 1992
Oil absorption	20 g/100g (±5 gm)	IS 33 1992
pH of aqueous extract	6 - 8	IS 33 1992
Moisture content	Max. 1.0 %	IS 33 1992
Residue on sieve ( 45 µm )	Max. 0.5%	IS 33 1992
Water soluble salts	Max. 1.0%	IS 33 1992
Conductivity	Max. 500 µS	IS 33 1992
Soluble Pb - content	Max. 5.0 %	ISO 3711

### Applications

Alkyd / Stoving	●
Industrial	●
Coil Coating	●
Automotive / Refinish / Road Marking	○
Powder Coating	●

- - Major use  
○ - Potential use

### Fastness Properties

Parameter	Values	Method
Heat Stability ( 5 min )	220°C - 240°C	VX/FP/002
Acid resistance ( 1 - 5 )	4	IS 2932
Alkali resistance ( 1 - 5 )	1	IS 2932
Light Fastness ( 1 - 8 )		
Full shade	6-7	IS 33 1992
Weather Fastness ( 1 - 5 )		
Full shade	3	ISO 11341
Resistance to Sulphur dioxide(1 - 5)	2	ISO-3231

VOXCO® is a registered trademark of VOXCO Pigments and Chemicals Pvt Ltd. Above stated product specification and application information are based on our current laboratory report. They are non-binding and do not have any guarantee. The processing company must establish the suitability of individual product before using. As the use of processing company lies beyond our knowledge and control, we cannot accept any liability relating to the use of our product in particular application.